



Terry Seal WP™

Terry Asphalt Materials Inc. – 8600 Berk Blvd. – Hamilton, Ohio – 45015

PHYSICAL CHARACTERISTICS COMPOSITION STANDARDS / ACTUALS

	<u>Spec. limits</u>	<u>Typical Results</u>
➤ Viscosity SFS @ 50° C	75 - 400	130
➤ Asphalt Oil Content	Minimum 62%	65.0+/-3.0%
➤ Demulsability	Minimum 60	75+
➤ Residue Penetration	100 - 200	125-150

PRODUCT NAME

Terry Seal WP™

MANUFACTURER

Terry Asphalt Materials Inc.
8600 Berk Blvd.
Hamilton, Ohio 45015

PH: 513-874-6192

FAX: 513-874-6540

Additional Plant Locations

1950 Williams Street
Alma, Michigan 48801

PH: 989-463-1323

FAX: 989-466-2838

PRODUCT DESCRIPTION

Terry Seal WP™ is a high performance asphalt emulsion designed for spray patch repairs of asphalt and concrete pavements in cooler months or climatic conditions.

Availability: Bulk available at terminal or tanker load delivery.

Color: Terry Seal WP™ binder and suitable aggregate will typically result in a black asphaltic mixture, which weathers to a surface color of the stone used.

Basic Uses: The Maintenance of roads and other asphalt pavements such as pothole patching and other spray seal patch operations.

Composition: As shipped, Terry Seal WP™ is an asphalt emulsion. Minimum 62% solids.

Limitations: Do not allow to freeze or boil.

INSTALLATION

Preparatory Work: Surface should be clean and free of all loose material, dirt and dust.

Methods: May be spray applied by suitable mechanized equipment.

Mix Design: Use full strength. For a typical spray patch application, material can be sprayed in alternating layers to produce a uniform sealed surface, with cover aggregate as last layer.

Precautions: Hot liquid. Consult material safety data sheet for specific handling and safety precautions.

MAINTENANCE

Tools and equipment may be cleaned with T.H.A.T Cleaner™.

TECHNICAL DATA

Environmental Considerations: Terry Seal WP™ is considered non-hazardous. It is a water-based material containing less than 30 g/L (.24 lbs./gal.) VOC content.

Physical Composition: As supplied, Terry Seal WP™ meets the standard specification for emulsified asphalts, ASTM D977.

Drying Time: Varies with weather conditions.

Non-Flammability: This product shows no tendency to flash or ignite.

TECHNICAL SERVICES

Material safety data sheets, as well as test results and field service are available upon request.

OTHER AVAILABLE PRODUCTS :

Anionic Emulsions

Cationic Emulsions

Asphalt Cements

Polymer Modified Asphalt Cements

T.H.A.T. Asphalt Cleaner™

WARRANTY

Terry Seal WP™ as shipped from the manufacturer, is warranted to meet all composition and performance criteria as stated in previous section under Technical Data. If there is any determination to the contrary, purchase price of the material will be refunded.

The information contained herein is correct to the best of our knowledge. The recommendations or suggestions contained in this bulletin are made without guarantee or representation as to results. Users should evaluate these recommendations and suggestions in their own laboratories prior to use. Terry Materials' responsibility for claims arising from breach of warranty, negligence or otherwise is limited to the purchase price of the material. Freedom to use any patent, trademark, or service mark owned by Terry Industries or any of its affiliate companies or others is not to be inferred from any statement or suggestion contained herein.